

## EPITAXIAL GROWTH METHOD FOR ATOMIC LAYER OF III-V COMPOUND SEMICONDUCTOR

## EPITAXIAL GROWTH METHOD FOR ATOMIC LAYER OF III-V COMPOUND SEMICONDUCTOR

Patent Number: JP63222420  
Publication date: 1988-09-16  
Inventor(s): USUI AKIRA  
Applicant(s): NEC CORP  
Requested Patent: ☐ JP63222420  
Application Number: JP19870055172 19870312  
Priority Number(s):  
IPC Classification: H01L21/205  
EC Classification:  
EC Classification:  
Equivalents: JP1891052C, JP6020046B

### Abstract

**PURPOSE:** To make it possible to grow high quality regular mixed crystals and a superlattice structure, by forming a group III element absorbing layer on a substrate crystal, then repeating the supplying process of a group VI element for a specified time, and thereafter supplying the chlorides of a group V element and a group III element alternately.

**CONSTITUTION:** A substrate crystal 6 is put in a reaction chamber 5. The growing temperature is increased in a PH<sub>3</sub> stream. HCl is supplied in the reaction chamber 3. After a specified time, the crystal is moved into a reaction chamber 3. The crystal is exposed to InCl for five seconds and the InCl is absorbed. Then the crystal 6 is returned into the reaction chamber 5. The surface is exposed to an H<sub>2</sub>Se atmosphere for five seconds. The crystal 6 is moved into the reaction chamber 3. This cycle is repeated by several tens of times. The movement of crystals 6 is repeated in the sequence of InCl-AsH<sub>3</sub>-GaCl-AsH<sub>3</sub>. A GaAs/InAs regular mixed crystal having high resistance is grown. Then a non-doped GaAs/InAs regular mixed crystal is grown. Thus the high quality regular mixed crystals and a superlattice structure can be grown.